

Macroporous Type I Strong Base Anion Exchange Resin

**Basic Features:**

Application	Demineralization - High Operating Capacity - Uniformly Sized
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type 1 Quaternary Ammonium
Ionic form as shipped	Cl <sup>-</sup>

**Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Cl <sup>-</sup>	1 eq/l
Total Capacity (min.)	Cl <sup>-</sup>	21.83 kGr/ft <sup>3</sup>
Moisture Retention	Cl <sup>-</sup>	61-66 %
Mean Size Typical		0.52-0.62 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	Cl <sup>-</sup> → OH <sup>-</sup>	20 %
Specific Gravity		1.08 g/ml
Shipping Weight (approx.)		670-690 g/l
Temp Limit	OH <sup>-</sup>	60 °C
Temp Limit	OH <sup>-</sup>	140 °F
Temp Limit	Cl <sup>-</sup>	100 °C
Temp Limit	Cl <sup>-</sup>	212 °F
pH Limits		0-14 (Stability)
pH Limits	H <sup>+</sup>	0-11 (Operating)

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com