

Macroporous Weak Base Anion Exchange Resin

Purolite A100S is a macroporous polystyrenic weak base anion resin having tertiary amine functionality especially prepared for use in the sugar and sweetener industry. Purolite A100S is designed to exhibit high operating capacity. Because of its special porosity characteristics Purolite A100S shows excellent properties for removal of naturally occurring organic species along with superior elution efficiency of the organics during regeneration. Purolite A100S also shows excellent resistance to osmotic shock as well as being physically resistant to mechanical breakage. Regeneration with caustic soda requires only 125% of the stoichiometric equivalent when related to the ionic loading on the resin at the exhaustion point. The rinse characteristics are good and minimum volumes of decationized water are required to rinse down to a conductivity of 50  $\mu\text{S/cm}$ .

**Basic Features:**

Application	Demineralization of Sugar Solutions
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Tertiary Amine
Ionic form as shipped	Free Base

**Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Free Base	1.30 eq/l
Total Capacity (min.)	Free Base	28.38 kGr/ft <sup>3</sup>
Moisture Retention	Cl <sup>-</sup>	53-60 %
SBC		10-20 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	FB → Cl <sup>-</sup>	20 %
Specific Gravity		1.04 g/ml
Shipping Weight (approx.)		655-685 g/l
Shipping Weight (approx.)		40.9-42.8 lbs/ft <sup>3</sup>
Temp Limit	OH <sup>-</sup>	60 °C
Temp Limit	OH <sup>-</sup>	140 °F
Temp Limit	Cl <sup>-</sup>	100 °C
Temp Limit	Cl <sup>-</sup>	212 °F

USA  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

Europe  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

Asia Pacific  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com

pH Limits		0-14 (Stability)
pH Limits	H <sup>+</sup>	0-9 (Operating)

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: [info@puroliteusa.com](mailto:info@puroliteusa.com)

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: [sales@purolite.com](mailto:sales@purolite.com)

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: [pultalan@purolitechina.com](mailto:pultalan@purolitechina.com)