

Macroporous Intermediate Base Anion Exchange Resin

**Basic Features:**

Application	Demineralization of Sugar Solutions
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Tertiary Amine
Ionic form as shipped	Free Base

**Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Free Base	1.10 eq/l
Total Capacity (min.)	Free Base	24.02 kGr/ft <sup>3</sup>
Moisture Retention	Cl <sup>-</sup>	58-65 %
SBC		10-20 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	FB → Cl <sup>-</sup>	22 %
Specific Gravity		1.02 g/ml
Shipping Weight (approx.)		645-675 g/l
Shipping Weight (approx.)		40.3-42.2 lbs/ft <sup>3</sup>
Temp Limit	OH <sup>-</sup>	60 °C
Temp Limit	OH <sup>-</sup>	140 °F
Temp Limit	Cl <sup>-</sup>	100 °C
Temp Limit	Cl <sup>-</sup>	212 °F
pH Limits		0-14 (Stability)
pH Limits	H <sup>+</sup>	0-9 (Operating)

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com