

Gel Type Strong Acid Cation Exchange Resin

Purolite® C100ELT is a high capacity premium bead form, conventional gel polystyrene sulphonate cation exchange resin, designed for use in industrial or house hold water conditioning equipment. It removes the hardness ions, e.g. calcium and magnesium, replacing them with sodium ions. When the resin bed is exhausted and hardness ions begin to break through, capacity is restored by regeneration with common salt. The capacity obtained depends largely on the amount of salt used in the regeneration. Purolite® C100ELT is also capable of removing dissolved iron, manganese, and also suspended matter by virtue of the filtering action of the bed.

Basic Features:

Application	Softening of Water - Light colored beads as C100E
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads - light colour
Functional Group	Sulphonic acid
Ionic form as shipped	Na ⁺

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Na ⁺	1.90 eq/l
Total Capacity (min.)	Na ⁺	41.48 kGr/ft ³
Moisture Retention	Na ⁺	46-50 %
Mean Size Typical		0.60-0.85 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	Na ⁺ → H ⁺	10 %
Reversible Swelling (max.)	Ca ₂ ⁺ → Na ⁺	8 %
Specific Gravity		1.27 g/ml
Shipping Weight (approx.)		800-840 g/l
Shipping Weight (approx.)		50-52.5 lbs/ft ³
Temp Limit	H ⁺	120 °C
Temp Limit	H ⁺	250 °F
Temp Limit	Na ⁺	140 °C
Temp Limit	Na ⁺	285 °F

USA
 Telephone: (1) 610-668-9090
 Fax: (1) 610-668-8139
 Email: info@puroliteusa.com

Europe
 Telephone: +44 1443 229334
 Fax: +44 1443 227073
 Email: sales@purolite.com

Asia Pacific
 Telephone: +86 571 876 31385
 Fax: +86 571 876 31385
 Email: pultalan@purolitechina.com

pH Limits

0-14

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com