

Gel Type Strong Acid Cation Exchange Resin

**Basic Features:**

Application	Treatment Of Sugar Solutions
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic acid
Ionic form as shipped	Na <sup>+</sup>

**Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Na <sup>+</sup>	2.10 eq/l
Total Capacity (min.)	Na <sup>+</sup>	44.80 kGr/ft <sup>3</sup>
Moisture Retention	Na <sup>+</sup>	43 - 47 %
Mean Size Typical		0.65 - 0.9 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	Na <sup>+</sup> → H <sup>+</sup>	8 %
Specific Gravity		1.29 g/ml
Shipping Weight (approx.)		815 - 850 g/l
Shipping Weight (approx.)		50.9 - 53.1 lbs/ft <sup>3</sup>
Temp Limit	H <sup>+</sup>	120 °C
Temp Limit	H <sup>+</sup>	250 °F
Temp Limit	Na <sup>+</sup>	140 °C
Temp Limit	Na <sup>+</sup>	285 °F
pH Limits		0 - 14

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com