

Macroporous Strong Acid Cation Exchange Resin

**Basic Features:**

Application	Dem mineralization - Counter Flow - Narrow Size Grading
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic acid
Ionic form as shipped	H <sup>+</sup>

**Typical Physical and Chemical Characteristics:**

Total Capacity (min.)	Na <sup>+</sup>	1.80 eq/l
Total Capacity (min.)	Na <sup>+</sup>	39.30 kGr/ft <sup>3</sup>
Moisture Retention	H <sup>+</sup>	54-59 %
Mean Size Typical		0.60-0.70 mm
Uniformity Coefficient (max.)		1.20
Reversible Swelling (max.)	Na <sup>+</sup> → H <sup>+</sup>	4 %
Specific Gravity		1.18 g/ml
Shipping Weight (approx.)		730-770 g/l
Shipping Weight (approx.)		45.6-48.1 lbs/ft <sup>3</sup>
Temp Limit	H <sup>+</sup>	120 °C
Temp Limit	H <sup>+</sup>	250 °F
Temp Limit	Na <sup>+</sup>	140 °C
Temp Limit	Na <sup>+</sup>	285 °F
pH Limits		0-14

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com