

Product Data Sheet

PUROLITE® MB400

Mixed Bed

Mixed Bed Exchange Resin

Purolite MB400 is a high quality resin mixture for direct purification of water. It is suitable for use in regenerable or nonregenerable cartridges and in large ion exchange units. Passage of water at recommended flow rates through the resin as supplied can achieve almost complete reduction of total dissolved solids. The residuals produce average conductivity values of about 0.1 µs cm-1 for a major portion of the service run which may be extended depending upon the final water quality acceptable. Equivalent volumes of ultra pure water may be obtained after regeneration but only if sufficient regenerant quantities are employed to achieve the percentage conversion levels equivalent to those of the "as supplied" resin. Generally acceptable capacity and quality is obtained economically at lower regeneration

Basic Features:

Application Demineralization - High Purity Silica Free

Polymer Structure Gel polystyrene crosslinked with divinylbenzene

Appearance Spherical beads

Functional Group Sulphonic Acid and Type 1 Quaternary Ammonium

Ionic form as shipped H^+/OH^-

Typical Physical and Chemical Characteristics:

Cation Component		Gel Strong Acid Cation
Anion Component		Gel Strong Base Anion
Cation / Anion Ratio		40 / 60 %
Total Capacity (min.)	Na ⁺	1.90 eq/l
Total Capacity (min.)	Na ⁺	41.50 kGr/ft ³
Total Capacity (min.)	Cl	1.30 eq/l
Total Capacity (min.)	Cl	28.40 kGr/ft ³
Moisture Content		65 %
Mean Size Typical		0.60-0.85 mm
Uniformity Coefficient (max.)		1.70
Shipping Weight (approx.)		705-740 g/l
Shipping Weight (approx.)		44.1-46.3 lbs/ft ³
Temp Limit	Non ⁻ Regenerable Bed	100 °C
Temp Limit	Non ⁻ Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139

Email: info@puroliteusa.com

Telephone: +44 1443 229334

Fax: +44 1443 227073

Email: sales@purolite.com

Asia Pacific

Telephone: +86 571 876 31385 Fax: +86 571 876 31385

Email: pultalan@purolitechina.com



Product Data Sheet

PUROLITE® MB400

Mixed Bed

Temp Limit	Regenerable Bed	140 °F	
pH Limits		0-14	

USA

Telephone: (1) 610-668-9090 Fax: (1) 610-668-8139 Email: info@puroliteusa.com Europe

Telephone: +44 1443 229334 Fax: +44 1443 227073 Email: sales@purolite.com Asia Pacific

Telephone: +86 571 876 31385 Fax: +86 571 876 31385 Email: pultalan@purolitechina.com