

Mixed Bed Exchange Resin - Self Indicating

Purolite MB450 VC is a resin mixture for direct purification of water of the highest quality. This resin mixture changes colour from emerald green to deep blue on exhaustion. It is suitable for use in regenerable or non-regenerable cartridges or in large ion exchange units. Passage of water at recommended flow rates through the resin, as supplied, can achieve almost complete reduction of total dissolved solids. The residuals produce average conductivity values of about 0.1 µS/cm for a major portion of the service run. However it will be necessary to cease water production prior to complete colour change if highest quality water is essential. Generally water with a conductivity between 5-50 µS/cm is obtained when the blue colour reaches close to the bottom of the bed. It should be noted that at the end of the run, water of low pH can be produced. Equivalent volumes of pure water may be obtained after regeneration but only if sufficient regenerant quantities are employed to achieve the percentage conversion levels close to those of the "as supplied" resin. Generally acceptable capacity and quality is obtained economically at lower regeneration levels. Self indication may only be possible for several cycles.

Basic Features:

Application	Demineralization - High Purity Silica Free
Polymer Structure	Gel/Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic Acid and Type 1 Quaternary Ammonium
Ionic form as shipped	H / OH

Typical Physical and Chemical Characteristics:

Cation Component	Gel Strong acid cation	
Anion Component	Macroporous strong base anion	
Cation / Anion Ratio	40 / 60 %	
Total Capacity (min.)	Na ⁺	1.90 eq/l
Total Capacity (min.)	Na ⁺	41.50 kGr/ft ³
Total Capacity (min.)	Cl ⁻	1.15 eq/l
Total Capacity (min.)	Cl ⁻	25.10 kGr/ft ³
Moisture Content	65 %	
Mean Size Typical	0.60-0.85 mm	
Uniformity Coefficient (max.)	1.70	
Shipping Weight (approx.)	700-735 g/l	
Shipping Weight (approx.)	43.7-45.9 lbs/ft ³	

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com

Temp Limit	Non-Regenerable Bed	100 °C
Temp Limit	Non-Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com