

Mixed Bed Exchange Resin - Self Indicating

Purolite MB46IND is a special high quality resin mixture for direct purification of water. This resin mixture changes color from blue-green to amber on exhaustion. The ratio of component resins has been specifically tailored to provide a high capacity for cations removable. It is therefore recommended where waters which contain bicarbonate, carbonate or even hydroxide ions are being treated, or where the limiting factor in performance could be kinetics of the cation resin. Waters which contain traces of iron or other metal corrosion contamination also benefit from treatment using this resin mixture. Purolite MB46IND is suitable for use in regenerable or non-regenerable cartridges and other ion exchange units. Passage of water at recommended flow rates through the resin as supplied can achieve almost complete reduction of total dissolved solids during the operation cycle. The residuals produce average conductivity values of less than 2 µs/cm for a major portion of the service run which may be extended depending upon the final water quality acceptable. However it will be necessary to cease water production shortly prior to complete color change if highest quality water is essential. Almost equivalent volumes of pure water of identical quality may be obtained after regeneration but only if sufficient regenerant quantities are employed to achieve the percentage conversion levels equivalent to those of the "as supplied" resin. Generally acceptable capacity and quality is obtained economically at lower regeneration levels.

Basic Features:

Application	EDM Applications - High Capacity
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic Acid and Type 1 Quaternary Ammonium
Ionic form as shipped	H ⁺ / OH ⁻

Typical Physical and Chemical Characteristics:

Cation Component		Gel Strong Acid Cation
Anion Component		Gel Strong Base Anion
Cation / Anion Ratio		50 / 50 %
Total Capacity (min.)	Na ⁺	2.00 eq/l
Total Capacity (min.)	Na ⁺	43.70 kGr/ft ³
Total Capacity (min.)	Cl ⁻	1.40 eq/l
Total Capacity (min.)	Cl ⁻	30.60 kGr/ft ³
Moisture Content		60 %
Mean Size Typical		0.60-0.85 mm
Uniformity Coefficient (max.)		1.70
Shipping Weight (approx.)		720-750 g/l

USA
 Telephone: (1) 610-668-9090
 Fax: (1) 610-668-8139
 Email: info@puroliteusa.com

Europe
 Telephone: +44 1443 229334
 Fax: +44 1443 227073
 Email: sales@purolite.com

Asia Pacific
 Telephone: +86 571 876 31385
 Fax: +86 571 876 31385
 Email: pultalan@purolitechina.com

Shipping Weight (approx.)		45-46.9 lbs/ft ³
Temp Limit	Non-Regenerable Bed	100 °C
Temp Limit	Non-Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F
pH Limits		0-14

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com