

Mixed Bed Exchange Resin - Light Cation

Purolite MB600LT is a special high quality resin mixture of a light gel strong acid cation resin and a high capacity gel type I strong base anion resin for direct purification of water. It is suitable for use in regenerable or non-regenerable cartridges and in large ion exchange units. Passage of water at recommended flow rates through the resin as supplied can achieve almost complete reduction of total dissolved solids. The residuals produce average conductivity values of about 0.1 µS/cm for a major portion of the service run which may be extended depending upon the final water quality acceptable. The selection of a high capacity type I strong base anion resin ensures that Purolite MB-600LT has an excellent operating capacity. Equivalent volumes of purified water may be obtained after regeneration but only if sufficient regenerant quantities are employed to achieve the percentage conversion levels equivalent to those of the "as supplied" resin. Generally acceptable capacity and quality is obtained economically at lower regeneration levels.

**Basic Features:**

Application	Demineralization - High Purity Silica Free
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic Acid and Type 1 Quaternary Ammonium
Ionic form as shipped	H <sup>+</sup> / OH <sup>-</sup>

**Typical Physical and Chemical Characteristics:**

Cation Component	Gel Strong Acid Cation	
Anion Component	Gel Strong Base Anion	
Cation / Anion Ratio	40 / 60 %	
Total Capacity (min.)	Na <sup>+</sup>	1.90 eq/l
Total Capacity (min.)	Na <sup>+</sup>	41.50 kGr/ft <sup>3</sup>
Total Capacity (min.)	Cl <sup>-</sup>	1.40 eq/l
Total Capacity (min.)	Cl <sup>-</sup>	30.60 kGr/ft <sup>3</sup>
Moisture Content	65 %	
Mean Size Typical	0.60-0.85 mm	
Uniformity Coefficient (max.)	1.70	
Shipping Weight (approx.)	715-750 g/l	
Shipping Weight (approx.)	44.7-46.9 lbs/ft <sup>3</sup>	
Temp Limit	Non-Regenerable Bed	100 °C

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com

Temp Limit	Non-Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F
pH Limits		0-14

**USA**  
Telephone: (1) 610-668-9090  
Fax: (1) 610-668-8139  
Email: info@puroliteusa.com

**Europe**  
Telephone: +44 1443 229334  
Fax: +44 1443 227073  
Email: sales@purolite.com

**Asia Pacific**  
Telephone: +86 571 876 31385  
Fax: +86 571 876 31385  
Email: pultalan@purolitechina.com