

Nuclear Grade Mixed Bed Exchange Resin

Purolite NRW37 Li is a nuclear grade mixed bed resin especially designed for the removal of radioactive contaminants from primary circuits of nuclear power plants conditioned with natural lithium hydroxide. The product is an equilibrium mixture (chemical equivalents) of Purolite NRW100 carefully converted to the high purity natural lithium form, and Purolite NRW400 which is supplied highly converted to the hydroxide form. The mixture is capable of removing both cationic and anionic contaminants while maintaining the concentration of lithium hydroxide conditioner at near the correct dose level within the sealed circuit. All Purolite nuclear resins are supplied to exacting standards of high purity as given in the specifications below.

Basic Features:

Application	Decontamination of Pressurized Water Reactor (PWR) Circuits
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Sulphonic Acid and Type 1 Quaternary Ammonium
Ionic form as shipped	Li ⁺ / OH ⁻

Typical Physical and Chemical Characteristics:

Cation Component		Gel strong acid cation
Anion Component		Gel strong base anion
Cation / Anion Ratio		40/60 %
Total Capacity (min.)	H ⁺	1.80 eq/l
Total Capacity (min.)	H ⁺	39.30 kGr/ft ³
Total Capacity (min.)	OH ⁻	1.00 eq/l
Total Capacity (min.)	OH ⁻	21.80 kGr/ft ³
Moisture Content		65 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Shipping Weight (approx.)		720-750 g/l
Shipping Weight (approx.)		45-46.9 lbs/ft ³
Temp Limit	Non-Regenerable Bed	100 °C

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com

Temp Limit	Non-Regenerable Bed	212 °F
Temp Limit	Regenerable Bed	60 °C
Temp Limit	Regenerable Bed	140 °F
pH Limits		0-14
Cationic Form (min.)		99.90 %
Anionic Form (min.)	OH ⁻	95 %
Anionic Form (max.)	CO ₃ ⁻	5 %
Anionic Form (max.)	Cl ⁻	0.10 %
Anionic Form (max.)	SO ₄ ⁻	0.30 %
Impurities Sodium (max.)		30 ppm
Impurities Iron (max.)		80 ppm
Impurities Heavy Metals		40 ppm

USA

Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe

Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific

Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com