

CHELATING RESIN FOR COPPER REMOVAL

Purolite S930 is a macroporous polystyrene based chelating resin, with iminodiacetic groups designed for the removal of cations of heavy metals from industrial effluents. These cations may be separated from high concentrations of univalent cations (typically sodium) and also from common divalent cations (such as calcium). Removal can be achieved both from weakly acidic and weakly basic solutions depending on the metals to be removed. Purolite S930 finds use in processes for extraction and recovery of metals from ores, galvanic plating solutions, pickling baths, and effluents even in the presence of alkaline earth metals (calcium and magnesium). Further important uses include the refining of the salt solutions of transition and precious metals and for the cleaning and purification of various organic or inorganic chemical products by removal of heavy metals contamination (usually from aqueous solution).

Basic Features:

Application	Copper Removal
Polymer Structure	Macroporous crosslinked polymer
Appearance	Spherical beads
Functional Group	Iminodiacetic
Ionic form as shipped	Na

Typical Physical and Chemical Characteristics:

Copper Capacity min.	30 g/l
Moisture Retention (Na)	55-65 %
Mean Size Typical	0.60-0.85 mm
Uniformity Coefficient (max.)	1.50
Swelling H->Namax	20
Specific Gravity	1.13 g/ml
Shipping Weight (approx.)	710-745 g/l
Temp Limit	H ⁺ 70 °C
Temp Limit	H ⁺ 158 °F
pH Limits	0-14 (Stability)
pH Limits	2-6 (H Form)6-11 (Na Form) (Operating)

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com