

Macroporous Type I Strong Base Anion Exchange Resin

Purolite **PPA500MB** is a macroporous poly(vinylbenzyl-trimethylammonium) type I strong base anion exchange resin which because of its regeneration efficiency has particularly high operating capacity at lower or even moderate regeneration levels. It has superior kinetic properties and is also relatively less susceptible to organic fouling than are standard macroporous type strong base anion resins. Consequently higher purity treated water (or other solution) can generally be obtained. These useful advantages are obtained by way of the narrow particle size distribution. Purolite **PPA500MB** shows enhanced resistance to osmotic and thermal shock and good reversible sorptive capacity for the complex organic materials, both ionised and un-ionized, which occur in many surface water supplies. Its resistance to fouling is superior to that of both gel resins and many other typical standard macroporous resins. Excellent results may be obtained with this resin in most of the usual ion-exchange column configurations. In conventional two-stage deionizing plants, its silica-removal properties are superior to those of most premium strong-base anion exchange resins. With influent solutions containing relatively high proportions of bicarbonate and sulphate, working capacities as high as 80% of the total exchange capacity can be achieved. Purolite **PPA500MB** is especially designed for the use in mixed bed applications.

Basic Features:

Application	Fast Regeneration Efficient Demineralization - Uniformly Sized
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	
Ionic form as shipped	Cl ⁻

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Cl ⁻	1.15 eq/l
Total Capacity (min.)	Cl ⁻	25.11 kGr/ft ³
Moisture Retention	Cl ⁻	53 - 58 %
Mean Size Typical		0.52 - 0.62 mm
Uniformity Coefficient (max.)		1.50
Reversible Swelling (max.)	Cl ⁻ → OH ⁻	15 %
Specific Gravity		1.08 g/ml
Shipping Weight (approx.)		670 - 690 g/l
Temp Limit	OH ⁻	65 °C
Temp Limit	OH ⁻	150 °F

USA
 Telephone: (1) 610-668-9090
 Fax: (1) 610-668-8139
 Email: info@puroliteusa.com

Europe
 Telephone: +44 1443 229334
 Fax: +44 1443 227073
 Email: sales@purolite.com

Asia Pacific
 Telephone: +86 571 876 31385
 Fax: +86 571 876 31385
 Email: pultalan@purolitechina.com

PUROLITE® PPA500MB
Strong Base Anion Macroporous

Temp Limit	Cl ⁻	100 °C
Temp Limit	Cl ⁻	212 °F
pH Limits		0 - 14 (Stability)
pH Limits	H ⁺	0 - 11 (Operating)

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com