

Gel Type I Strong Base Anion Exchange Resin

Purolite A600MB is a strong-base anion exchanger with both high operating capacity and the ability to achieve low residual silica levels. It has a clear gel structure, showing excellent regeneration efficiency over a wide range of regeneration levels, together with good rinse characteristics. Purolite A600 functions well both in mixed bed and layered bed demineralizer systems, where specially tailored particle size ranges result in achieving or maintaining good separations. Purolite A600MB has exceptional physical stability for a conventional gel-type resin which permits a long life without the development of excessive pressure drop; it also shows good kinetics of exchange, enabling very low concentration levels of both strong and weak acid anions to be achieved at practical flowrates.

Basic Features:

Application	Efficient Demineralization / Silica Removal - Mixed Beds
Polymer Structure	Gel polystyrene crosslinked with divinylbenzene
Appearance	Spherical beads
Functional Group	Type 1 Quaternary Ammonium
Ionic form as shipped	Cl ⁻

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Cl ⁻	1.40 eq/l
Total Capacity (min.)	Cl ⁻	30.57 kGr/ft ³
Moisture Retention	Cl ⁻	43-48 %
Mean Size Typical		0.65-0.90 mm
Uniformity Coefficient (max.)		1.70
Reversible Swelling (max.)	Cl ⁻ → OH ⁻	20 %
Specific Gravity		1.09 g/ml
Shipping Weight (approx.)		685-720 g/l
Shipping Weight (approx.)		42.8-45 lbs/ft ³
Temp Limit	OH ⁻	60 °C
Temp Limit	OH ⁻	140 °F
Temp Limit	Cl ⁻	100 °C
Temp Limit	Cl ⁻	212 °F
pH Limits		0-14 (Stability)
pH Limits	OH ⁻	1-10 (Operating)

USA
 Telephone: (1) 610-668-9090
 Fax: (1) 610-668-8139
 Email: info@puroliteusa.com

Europe
 Telephone: +44 1443 229334
 Fax: +44 1443 227073
 Email: sales@purolite.com

Asia Pacific
 Telephone: +86 571 876 31385
 Fax: +86 571 876 31385
 Email: pultalan@purolitechina.com