

Basic Features:

Application	Removal for CS ₂ removal during manufacturing Isoprene rubber
Polymer Structure	Macroporous polystyrene crosslinked with divinylbenzene
Appearance	Spherical Beads
Functional Group	Complex amine
Ionic form as shipped	Free Base

Typical Physical and Chemical Characteristics:

Total Capacity (min.)	Free Base	1.60 eq/l
Moisture Retention	Cl ⁻	45 - 55 %
SBC		5% %
Reversible Swelling (max.)	FB → Cl ⁻	15 %
Specific Gravity		1.06 g/ml
Temp Limit	Cl ⁻	100 °C
Temp Limit	Cl ⁻	212 °F
pH Limits		0 - 14 (Stability)

USA
Telephone: (1) 610-668-9090
Fax: (1) 610-668-8139
Email: info@puroliteusa.com

Europe
Telephone: +44 1443 229334
Fax: +44 1443 227073
Email: sales@purolite.com

Asia Pacific
Telephone: +86 571 876 31385
Fax: +86 571 876 31385
Email: pultalan@purolitechina.com